



## HIGH PERFORMANCE THERMAL INTERFACE PRODUCTS

Tgard<sup>™</sup> 3000 is specifically designed to solve overheating issues such as lower component efficiency, premature component failures, size limitations and other performance problems for today's power component assemblies. The need to remove unwanted heat to ambient temperatures becomes more important as electronic systems pack more power into smaller spaces.

Tgard 3000 is a film-based product that is designed to resist cut through in screw mounting applications while providing a more consistent breakdown voltage over other insulator constructions. The soft conformal coating on the film core provides an excellent mating surface for low pressure clip mounting applications.

## PERFORMANCE CAPABILITIES

- High dielectric breakdown of 6,000 volts
- Film base resistant to cut through
- Thermal resistance of 0.55°C-in<sup>2</sup>/watt @ 50 psi pressure
- Thermal resistance of 0.37°C-in<sup>2</sup>/watt @ 400 psi pressure

## FEATURES AND BENEFITS

- Designed for switch mode power supply applications
- Reinforced with high temperature resistant film
- High voltage resistant film

## APPLICATIONS

- Switching mode power supplies for:
  - Communications
  - Consumer electronics
  - Industrial
  - Instrumentation
  - Medical
- Electrical power generators
- UPS units

# Tgard™ 3000 Series

## Thermally Conductive Insulators

PROPERTIES	TEST METHOD	METRIC VALUES		IMPERIAL VALUES			
<b>ELECTRICAL PROPERTIES</b>							
Dielectric with standard voltage 50mm probe for 30 sec	ASTM D149	4,500 volts AC		4,500 volts AC			
Dielectric breakdown voltage 50mm probe	ASTM D149	Avg >6,000 volts AC		Avg >6,000 volts AC			
Volume resistivity	ASTN D257	10 <sup>12</sup> ohm-cm		10 <sup>12</sup> ohm-in			
Dielectric constant @1Mhz	ASTN D257	3.3		3.3			
<b>MECHANICAL PROPERTIES</b>							
Thickness		0.13 mm		5 mils			
Hardness	ASTM D2240	80 Shore A		80 Shore A			
Tensile strength	ASTM D412	43.4 Mpa		6.3 Kpsi			
Elongation along width or length	ASTM D412	35%		35%			
Operating temperature range		-60° to 180°C		-76° to 356°F			
Color		Brown		Brown			
UL flammability rating	UL 94	V-0		V-0			
<b>PRESSURE</b>	<b>UNITS</b>	<b>10</b>	<b>25</b>	<b>50</b>	<b>100</b>	<b>200</b>	<b>400</b>
		(69)	(172)	(345)	(689)	(1379)	(2758)
<b>TOTAL THERMAL RESISTANCE</b>							
Modified ASTM D5470	°C-in <sup>2</sup> /watt	0.86	0.68	0.55	0.44	0.40	0.37
Modified ASTM D5470	°C-in <sup>2</sup> /watt	5.55	4.39	3.55	2.83	2.58	2.39
TO-220	°C/watt	1.36	1.08	0.91	0.83	0.78	0.74

- Configurations available:
- Sheet form, roll form and die-cut parts
  - Single-side, pressure-sensitive adhesive on request
- Standard options:
- Without adhesive (A0): 12 x 18" sheets, 12" x 65M, 12" x 30M roll or custom configuration
  - With adhesive (A1): 11.75 x 18" sheets, 11.75" x 30M roll or custom configuration
- Standard die cut parts: Standard part sizes for TO-220, TO-247, TO-3P, TO-3PL and TO-264
- Custom die cut parts: Custom configurations available with standard tolerance of 0.5mm (0.020"). Ability to handle drawings in multiple file formats. (.DXF and .DWG preferred)

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

THR-DS-Tgard-3000\_0614

Any information furnished by Laird and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird materials rests with the end user, since Laird and its agents cannot be aware of all potential uses. Laird makes no warranties as to the fitness, merchantability or suitability of any Laird materials or products for any specific or general uses. Laird, Laird Technologies, Inc or any of its affiliates or agents shall not be liable for incidental or consequential damages of any kind. All Laird products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2014 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird or any third party intellectual property rights. Document A15099-00 Rev. C 06/2014