

## Tgard<sup>™</sup> 500 Thermally Conductive Insulators



# THICKER THERMAL INSULATOR PAD PREVENTS ELECTRICAL SHORTS IN AUTOMOTIVE ELECTRONICS APPLICATIONS

Tgard™ 500 is a medium thermal performance insulator pad consisting of a ceramic filled high temperature silcone rubber coated on electrical grade fiberglass.

Tgard 500 is designed for applications that require tadditional thickenss to prevent electrical shrots form stamped aluminumheatskinks used in switching mode power supplies (SMPS) and debris from aluminum castings used in automotive motor controls.

#### **FEATURES AND BENEFITS**

- High breakdown voltage of > 6,000 volts AC
- Thermal resistance of 0.48° C-in2/watt at 50 psi
- Thermal resistance of 0.28º C-in2/watt at 400 psi
- Thick enough to encapsulate burrs of stamped heatskinks

#### **APPLICATIONS**

- Automotive motor controls
- Switching mode power supplies
- stamped aluminum heatsinks

Americas: +1.847 839.6907 IAS-AmericasEastSales@lairdtech.com

Europe: +44.1628.858941 IAS-EUSales@lairdtech.com Asia: ++86.21.5855.0827.127 IAS-AsiaSales@lairdtech.com CLV-customerservice@lairdtech.com www.lairdtech.com/thermal

### Thermally Conductive Insulators

PROPERTIES	TEST M	TEST METHOD		METRIC VALUES		IMPERIAL VALUES		
ELECTRICAL PROPERTIES								
Dielectric with standard voltage 50mm probe for 30 sec	ASTM	D149	4,500 volts AC		4,500 volts AC			
Dielectric breakdown voltage 50mm probe	ASTM	ASTM D149		Avg >6,000 volts AC			Avg >6,000 volts AC	
Volume resistivity	ASTN	ASTN D257		10 <sup>12</sup> ohm-cm			10 <sup>12</sup> ohm-in	
Dielectric constant @1Mhz	ASTN D257		3.3			3.3		
Electrical RTI temperature rating	UL746D		150ºC		302ºF			
MECHANICAL PROPERTIES								
Thickness			0.23 mm			0.009 in		
Hardness	ASTM	ASTM D2240		80 Shore A		80 Shore A		
Tensile strength	ASTM	ASTM D412		11.7 Mpa		1.7 Kpsi		
Elongation @ 45º to warp/fill	ASTM D412		20%		20%			
Elongation along width or lengt	h ASTM	ASTM D412		5%		5%		
Operating temperature range	perating temperature range		-60º to 180ºC			-76º to 356ºF		
Color				Brown			Brown	
UL flammability rating	UL	UL 94		V-0		V-0		
PRESSURE	UNITS	10 (69)	25 (172)	50 (345)	100 (689)	200 (1379)	400 (2758)	
TOTAL THERMAL RESISTANCE								
Modified ASTM D5470	ºC-in²/watt	0.81	0.70	0.48	0.33	0.30	0.28	
Modified ASTM D5470	ºC-cm²/watt	5.16	4.52	3.21	2.13	1.94	1.80	
T0-220	ºC/watt	1.29	1.01	0.95	0.79	0.77	0.76	

Standard thickness: 9 mils (0.229 mm)

Configurations available: • Sheet form, roll form and die-cut parts

• Single-side, pressure-sensitive adhesive on request

Standard options: • Without adhesive (A0): 12 x 18" sheets, 12" x 65M,

12" x 30M roll or custom configuration

• With adhesive (A1): 11.75 x 18" sheets, 11.75" x 30M roll

or custom configuration

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.